

SCHEDE TECNICHE MATERIALI**TABELLA-FILO-INOX-AISI-302**

Diametro mm	Tolleranza diametro	AISI 302 / 1.4310 X10CrNi18-8 N/mm²
$d \leq 0.20$	$\pm 0,005$	2200/2530
$0.20 < d \leq 0.30$	$\pm 0,005$	2150/2470
$0.30 < d \leq 0.40$	$\pm 0,008$	2100/2410
$0.40 < d \leq 0.50$	$\pm 0,008$	2050/2360
$0.50 < d \leq 0.65$	$\pm 0,008$	2000/2300
$0.65 < d \leq 0.80$	$\pm 0,010$	1950/2240
$0.80 < d \leq 1.00$	$\pm 0,010$	1900/2180
$1.00 < d \leq 1.25$	$\pm 0,015$	1850/2120
$1.25 < d \leq 1.50$	$\pm 0,015$	1800/2070
$1.50 < d \leq 1.75$	$\pm 0,015$	1750/2010
$1.75 < d \leq 2.00$	$\pm 0,015$	1700/1950
$2.00 < d \leq 2.50$	$\pm 0,015$	1650/1900
$2.50 < d \leq 3.00$	$\pm 0,020$	1600/1840
$3.00 < d \leq 3.50$	$\pm 0,020$	1550/1780
$3.50 < d \leq 4.25$	$\pm 0,025$	1500/1720
$4.25 < d \leq 5.00$	$\pm 0,025$	1450/1670
$5.00 < d \leq 6.00$	$\pm 0,025$	1400/1610
$6.00 < d \leq 7.00$	$\pm 0,030$	1350/1550
$7.00 < d \leq 8.50$	$\pm 0,030$	1300/1500
$8.50 < d \leq 10.00$	$\pm 0,035$	1250/1440