

SCHEDE TECNICHE MATERIALI**TABELLA-FILO-INOX-AISI-631**

Diametro mm	Tolleranza diametro	AISI 631 / 1.4568 X7CrNiAl17-7
$d \leq 0.20$	$\pm 0,005$	1975/2270
$0.20 < d \leq 0.30$	$\pm 0,005$	1950/2240
$0.30 < d \leq 0.40$	$\pm 0,008$	1925/2215
$0.40 < d \leq 0.50$	$\pm 0,008$	1900/2185
$0.50 < d \leq 0.65$	$\pm 0,008$	1850/2130
$0.65 < d \leq 0.80$	$\pm 0,010$	1825/2100
$0.80 < d \leq 1.00$	$\pm 0,010$	1800/2070
$1.00 < d \leq 1.25$	$\pm 0,015$	1750/2010
$1.25 < d \leq 1.50$	$\pm 0,015$	1700/1955
$1.50 < d \leq 1.75$	$\pm 0,015$	1650/1900
$1.75 < d \leq 2.00$	$\pm 0,015$	1600/1840
$2.00 < d \leq 2.50$	$\pm 0,015$	1550/1780
$2.50 < d \leq 3.00$	$\pm 0,020$	1500/1725
$3.00 < d \leq 3.50$	$\pm 0,020$	1450/1670
$3.50 < d \leq 4.25$	$\pm 0,025$	1400/1610
$4.25 < d \leq 5.00$	$\pm 0,025$	1350/1550
$5.00 < d \leq 6.00$	$\pm 0,025$	1300/1495
$6.00 < d \leq 7.00$	$\pm 0,030$	1250/1440
$7.00 < d \leq 8.50$	$\pm 0,030$	1200/1380
$8.50 < d \leq 10.00$	$\pm 0,035$	1150/1320